**INTENDED USE:** Dental finishing and polishing points intended as a medical device for the purpose of final polishing of all composite and ceramic restorations.

## TECHNIQUE

STEP 1: D-FINE Double Diamond Primary Polishers (purple)

- 1. Use a finishing diamond/carbide to contour the composite surface.
- 2. Select the appropriate D-FINE Double Diamond Primary Polisher.
- 3. Using a wiping motion, at 7,500-10,000 rpm, and with light to moderate pressure and water spray, apply the primary polisher to the restorative surface. A smooth silky surface will appear in approximately 30 seconds.

## STEP 2: D-FINE Double Diamond Final High Shine Polishers (orange)

- 1. Select the appropriate D-FINE Double Diamond Final High Shine Polisher.
- 2. Again, with light to moderate pressure and water spray, apply the Final High Shine Polisher to the restorative surface with a wiping motion, until a high gloss finish is achieved.

NOTE: Failure to follow this technique will lead to premature degradation of the polishers.

## RECOMMENDED STERII IZATION

D-FINE Double Diamond polishers should be steam autoclaved only up to 275°F/135°C. Product is not sold in sterile condition.

## CLINICIAN'S CHOICE

London, ON, Canada, N6A 1M6 • Brookfield, CT, USA, 06804 1-800-265-3444 • (519) 641-3066

CAUTION: U.S. Federal law restricts this device to sale by, or on the order of, a dentist



Emergo Europe Molenstraat 15 2513 BH, The Hagu The Netherlands